

# EnduraLam™ Tint

## Tinted Laminate Glass

### Applications

- Apartments
- Skylights
- Office Partitions
- Commercial buildings
- Anywhere safety glass is required



## Features


**EnduraLam** is a Grade A Safety Glass. It provides increased safety because it holds together if broken, reducing the likelihood of serious injury, whether in a vertical or overhead position. It can also offer increased security as the glass will generally remain in the frame after fracture. Laminated glass consists of two or more layers of glass, factory bonded together with a plastic interlayer.

Architects and designers can feature glass like never before — combining a wide choice of coloured interlayers to produce transparency and translucency. More than 17,000 transparent, translucent, or solid colours that create just the right look and ambience for any project.

Tinted Laminate has many benefits including improved solar control, reduced glare from the sun, improved privacy and originality in architectural design.

*Please ensure the current data sheet is consulted prior to specification. If in doubt please contact Woods Glass.*

# EnduraLam™ Tint



## Performance/ Specifying

EnduraLam Tint is a tinted laminated glass product and has the options of being toughened, heat strengthened and heat soaked. The Interlayer must be chosen depending on the functionality required and then the tint and any additional properties must be decided upon. EnduraLam can be used in combination with other Woods Glass products like ceramic frit (Keramo) and low-e glass (Infinit E). All glass must be engineered to specific code and design, please contact Woods Glass to find out more information.

## Cleaning/ Maintenance

Normally when cleaning glass, a vinegar-based glass cleaner or mild dish soap and water with a soft, lint-free cloth or paper products is recommended. A squeegee or soft cloth may be carefully used to dry the glass and help avoid water spots.

It is not recommended to use petroleum-based cleaners or solvents as they can streak the glass and weaken the seal between the glass and frame. Avoid washing in direct sunlight to reduce streaking on the glass.

Never use razor blades, steel wool, putty knives or abrasive pads as they may damage the glass, particularly on toughened glass.

## Range

Many different thicknesses and tints are available for EnduraLam. Some options are clear, bronze, blue, green, grey, red and white. Woods are able to supply many more colours so please contact us to discuss special requirements.

## Building Codes

AS/NZS2208 - Building safety glazing materials

## Glass Types

- Tinted

## Interlayers

### Polyvinyl Butyral (PVB)

This is the most common form of interlayer and is available in 0.38, 0.76, 1.1, and 1.52 mm thickness, but can be layered thicker.

### Ethylene Vinyl Acetate (EVA)

This is a newer interlayer which is available in 0.4, 0.8, 1.2, 1.6 mm thickness and can be layered thicker. It is ideal for laminating a range of special products including inserts in the laminate like photovoltaics.

### SentryGlas Plus (SGP)

This is a special high strength interlayer for barriers and structural glazing applications, which is more rigid than other interlayers.



### Auckland Office

+64 (0)9 525 3379

Fax: +64 (0)9 525 8200

enquiry.akl@woodsglass.co.nz

### Wellington Office and Factory

Phone: +64 (0)4 913 1999

Fax: +64 (0)4 939 4499

enquiry.wgtn@woodsglass.co.nz

### Christchurch Office and Factory

Phone: +64 (0)3 366 3733

Fax: +64 (0)3 365 6422

enquiry.chch@woodsglass.co.nz